



Pacific Wood Laminates, Inc.

**PROFACE™ MDO
Concrete Form
SPECIFICATION SHEET**

FACE SHEET

Arclin Overlays
333 MDO (MEDIUM DENSITY OVERLAY)

Resin Content	35%	Base Paper Weight	41# MSF	GSM	200
		Core Resin Weight	22# MSF	GSM	108
		Glue Line Weight	11# MSF	GSM	54
		Total Weight	74# MSF	GSM	362

PANEL FEATURES

Face Veneer	----	Fine Grain Proprietary Imported Hardwood (no wood patches)
Back Veneer	----	"C" Grade Douglas Fir Veneer
Inner Plies	----	"C" Grade Veneers
Resin	----	Phenolic Exterior Glue
Size	----	48" X 96"
Thickness	----	1/2 - 1 1/8
Edge Seal	----	Nox-Crete Edge Flex 645
Realease Agent	----	Nox-Crete Form Coating
Stamp	----	APA Trademark

SPAN TABLES

FACE GRAIN ACROSS SUPPORTS							ONE STEP	FACE GRAIN PARALELL TO SUPPORTS						
Support	3/4		17.5mm / 11/16		5/8		Support	3/4		17.5mm / 11/16		5/8		
Spacing	L/360	L/270	L/360	L/270	L/360	L/270	Spacing	L/360	L/270	L/360	L/270	L/360	L/270	
4"	5150	5150	4790	4790	4425	4425	4"	4510	4510	3890	3890	3530	3530	
8"	1980	1980	1885	1885	1769	1769	8"	1735	1735	1660	1660	1647	1647	
12"	975	975	840	840	868	868	12"	745	815	730	805	681	754	
16"	495	550	415	470	394	525	16"	325	430	315	420	286	382	
19.2"	300	380	250	325	233	311	19.2"	230	255	225	250	203	236	
24"	160	210	130	175	121	161	24"	120	160	115	155	103	137	